

DESCRIPTION

- a two component surface tolerant high solids, direct to metal high build polyamine adduct cured epoxy coating
- approved to APAS 2973
- conforms to AS/NZS 3750.14
- conforms to AS/NZS 4020:2005 factory made white only

PRINCIPAL CHARACTERISTICS

- maintenance coating for use in a wide range of industrial applications as a primer, build coat or finish coat
- tolerant to lower grades of steel preparation for atmospheric exposure
- excellent recoatability
- cures down to 0°C with Low Temperature (LT) Part B
- excellent abrasion resistance
- resistant to splash of alkali, mineral oils, solvents and dilute acids
- suitable for immersion in salt and fresh water
- suitable for sewerage immersion applications such as wet wells and storage tanks (both for steel and concrete substrates)
- can be applied to existing piling between tides or for new work
- can be exposed to water immersion shortly after application
- suitable with well-designed cathodic protection systems

COLOURS AND GLOSS

- AS 2700 Colour card, micaceous iron oxide colour range – gloss
- Factory colours: White, Black, N53 Grey Blue, Y14 Golden Yellow, MIO 802, MIO 814, MIO N53
- **Only factory manufactured colours are suitable for Immersion applications**

RECOMMENDED FILM THICKNESS (PER COAT)

	Minimum	Maximum	Typical
Dry film thickness microns	125	500	200
Wet film thickness microns	145	590	235
Theoretical spreading rate m ² /l	6.9	1.7	4.3

BASIC DATA AT 25°C

- solids content approx.....85% by volume
- mix ratio3A:1B by volume
- touch dry after3-4 hours (Std Part B)
2-3 hours (LT Part B)
- full cure5 days (Std Part B)
3 days (LT Part B)

SURFACE PREPARATION

- all surfaces to be coated must be clean, dry and free from chalking and contamination

PREVIOUS SUITABLE COAT

- dry and free from any contamination and sufficiently roughened if necessary
- oil and grease should be removed from all surfaces in accordance with AS 1627.1 solvent cleaning

MILD STEEL

- blast clean in accordance with AS 1627.4 to Sa 2½ minimum (AS 1627.9), surface profile 40-70 microns
- power tool clean in accordance with AS 1627.2 to St 2 minimum (AS 1627.9), (atmospheric exposure only)

GALVANISED STEEL

- lightly blast using an inert grit or power tool clean to achieve a roughened uniform flat appearance (atmospheric exposure only)
- if oxidation occurs between blasting and application, the surface should be reblasted to the specified visual standard
- surface defects revealed by the blast cleaning process should be ground, filled or treated in the appropriate manner
- substrate temperature must be at least 5°C during application and 3°C above dew point
- relative humidity should not exceed 85%

CONCRETE

- must be free from bond breakers, curing agents or any other contaminants that may interfere with adhesion
- acid etch to remove all laitance (atmospheric exposure only)
- blast clean to remove all laitance
- moisture content of concrete should be max. 4%
- ensure all new concrete is fully cured prior to coating. Typically this may take a minimum of 4-6 weeks

APPLICATION INSTRUCTIONS

- mixing ratio by volume: 3A:1B
- mix EpinameL DTM985 Part A with EpinameL DTM985/DTS680 Standard or Low Temperature (LT) Part B only
- induction time - none
- pot life at 25°C – 2 hours (Std Part B), 45 min (LT Part B)
- stir the components and mixed product well using a mechanical mixer
- the temperature of the mixed product must be above 15°C, otherwise extra thinner may be required to obtain application viscosity
- too much thinner will result in lower sag resistance and slower cure
- thinner should only be added after mixing the components
- freshly catalysed material should not be added to product that has been mixed for some time
- Valspar recommends the use of coating inspection reports in compliance with AS/NZS 3894.10,11,12 refer to Information Sheet I-20 for more information
- for recommendations outside those contained in this data sheet, refer to Valspar

APPLICATION METHODS

- **AIRLESS SPRAY**
 - recommended thinner..... Thinner L760
 - volume of thinner..... 0-5%
 - nozzle orifice approx. 0.53-0.58mm
(0.021-0.023 inch)
 - nozzle pressure..... 15 MPa (2100psi)
- **AIR SPRAY**
 - recommended thinner..... Thinner L760
 - volume of thinner..... 0-10%
 - nozzle orifice approx. 1.5-2.0mm
 - nozzle pressure..... 0.2-0.4 MPa (30-60 psi)
- **BRUSH/ROLLER**

Only for touch up and spot repair

 - recommended thinner Thinner L760
 - volume of thinner 0-10%
 - the maximum dry film thickness that can be achieved when brushing/rolling is 100 microns
- **CLEANING SOLVENT** Thinner L760
Note: In warmer conditions, replace some or all of Thinner L760 with Thinner L765 (slow thinner).
- If spraying for extended periods or if stopping work it is recommended to intermittently flush out spray lines.

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

ADDITIONAL DATA

Overcoating Tables

Overcoating interval for EpinameL DTM985 cured with Standard Part B when top coating with **EpinameL DTM985**

Interval	5 °C	15 °C	25 °C	35 °C
Min	16 hrs	6 hrs	3 hrs	2 hrs
Max	3 mths	3 mths	2 mths	2 mths

Overcoating interval for EpinameL DTM985 cured with LT Part B when top coating with **EpinameL DTM985**

Interval	5 °C	10 °C	15 °C	25 °C
Min	8 hrs	5 hrs	3 hrs	1½ hrs
Max	3 mths	2 mths	2 mths	1 mth

Overcoating interval for EpinameL DTM985 cured with Standard Part B when top coating with **two pack polyurethanes**

Interval	5 °C	15 °C	25 °C	35 °C
Min	16 hrs	8 hrs	4 hrs	2 hrs
Max	1 month			

Overcoating interval for EpinameL DTM985 cured with LT Part B when top coating with **two pack polyurethanes**

Interval	5 °C	10 °C	15 °C	25 °C
Min	8 hrs	6 hrs	4 hrs	2 hrs
Max	1 mth	1 mth	14 days	14 days

Overcoating interval for EpinameL DTM985 cured with Standard Part B when top coating with **Paracryl IF540 and SeaPro TC170**

Interval	5 °C	15 °C	25 °C	35 °C
Min	16 hrs	8 hrs	4 hrs	2 hrs
Max	1 mth	1 mth	14 days	7 days

Overcoating interval for EpinameL DTM985 cured with LT Part B when top coating with **Paracryl IF540 and SeaPro TC170**

Interval	5 °C	10 °C	15 °C	25 °C
Min	8 hrs	6 hrs	4 hrs	2 hrs
Max	14 days	14 days	7 days	7 days

Overcoating interval for EpinameL DTM985 cured with Standard Part B when top coating with **SeaPro TC90**

Interval	5 °C	15 °C	25 °C	35 °C
Min	2 hrs	2 hrs	1 hr	1 hr
Max	8 hrs	6 hrs	4 hrs	2 hrs

Overcoating interval for EpinameL DTM985 cured with LT Part B when top coating with **SeaPro TC90**

Interval	5 °C	10 °C	15 °C	25 °C
Min	2 hrs	2 hrs	1 hr	½ hr
Max	4 hrs	3 hrs	2 hrs	1 hr

* surface must be dry and free from chalking and contamination prior to overcoating. If overcoating interval is exceeded, the surface must be dry and free from chalking and contamination and sufficiently roughened

Curing and Potlife Table for EpinameL DTM985 Cured with Standard Part B

Paint temperature	5 °C	15 °C	25 °C	35 °C
Dry to handle	24 hrs	10 hrs	5 hrs	3 hrs
Full cure	14 days	7 days	5 days	3 days
Potlife (at application viscosity)	8 hrs	4 hrs	2 hrs	1 hr

Curing and Potlife Table for EpinameL DTM985 Cured with LT Part B

Paint temperature	5 °C	15 °C	25 °C	35 °C
Dry to handle	12 hrs	5 hrs	3 hrs	NR
Full cure	12 days	5 days	3 days	NR
Potlife (at application viscosity)	3 hrs	1½ hrs	45 mins	NR

- adequate ventilation must be continuously maintained during application and curing
- suitable for application between tides, allow 30 minutes set up time before immersion
- coating will continue to cure when immersed in water
- premature exposure to water may cause colour or gloss change but will not affect the coating performance

PRECAUTIONS

- for recommendations outside those contained in this data sheet, refer to Valspar

PRODUCT COMPATIBILITY

Primers

- Galvit EP100
- Galvit EP102
- Galvit ES510
- Galvit ES600
- EpinameL CP502
- EpinameL PR250
- EpinameL PR360ZPS

Topcoats

- EpinameL DTM985
- Poly U400 (colours)
- Poly U750 (colours)
- Paracryl IF540 (colours)
- SeaPro TC170 Tiecoat
- SeaPro TC90

STORAGE AND PACKAGING

- shelf life at least 12 months
- all components shall be stored in a dry internal environment at between 5 °C and 35 °C
- packaging 20 Litre kit (15 Litre Part A, 5 Litre Part B), 4 Litre Kit (3 Litre Part A, 1 Litre Part B)
- product line: 2007

For the most up to date information visit our website or Contact Valspar Customer Service Hotline on:



Quality
ISO 9001

Valspar is committed to quality in the design, production and delivery of its products and services. Valspar's Australian manufacturing facilities quality management systems are certified to ISO9001.

www.wattylpc.com

132 101 (Australia) or 0800 735 551 (New Zealand)

Valspar's laboratory facilities are accredited for technical competence with the National Association of Tests Authorities, Australia (NATA) and comply with the requirements of ISO/IEC 17025. Accreditation No.104 (Footscray), 1154 (Glendenning) and 931 (Kilburn).



Trademarks are the property of Valspar Paint (Australia) Pty Ltd.

1. This information, provided by Valspar Paint (Australia) Pty Ltd (hereinafter referred to as "Valspar"), is important to ensure that the listed product(s) perform according to the stated application and uses and must be followed to meet Valspar's warranties express and implied. Valspar advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by Valspar and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Valspar endeavours to update this information and maintain the accuracy and currency of its contents, Valspar does not warrant that the information provided is current when the product is used or is wholly comprehensive. 3. For all product and non-product related information, Valspar recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Valspar office before using the product(s). 4. To the full extent permitted by law, Valspar's liability for breach of a condition or warranty implied into the contract for sale between Valspar and you by law is limited at Valspar's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required Valspar Technical Services shall be contacted prior to commencement. VALSPAR PAINT (AUSTRALIA) PTY LTD (ABN 40 000 035 914)